

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
29 September 2005 (29.09.2005)

PCT

(10) International Publication Number  
**WO 2005/090491 A1**

(51) International Patent Classification<sup>7</sup>: **C09D 5/02**, 7/12,  
5/28, 7/00, B05D 1/28, 1/40

(21) International Application Number:  
PCT/EP2005/002821

(22) International Filing Date: 15 March 2005 (15.03.2005)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
04075853.4 17 March 2004 (17.03.2004) EP

(71) Applicant (*for all designated States except US*):  
**AKZO NOBEL COATINGS INTERNATIONAL**  
B.V. [NL/NL]; Velperweg 76, NL-6824 BM Arnhem (NL).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **GUERRA, Antonio**  
[IT/IT]; Via Dei Boschi 10, 28040 Marano Ticino (IT).  
**PEZZUTO, Biagio** [IT/IT]; Via Mottarone 4, 28041 Arona  
(IT). **MANTELLINO, Ugo** [IT/IT]; Strada Commerciale  
Quara-Montereaggio 4, 28066 Galliate (IT).

(74) Agent: **SCHALKWIJK, Pieter, Cornelis**; Akzo Nobel  
N.V., Intellectual Property Dept. (Dept. AIP), P.O. Box  
9300, NL-6800 SB Arnhem (NL).

(81) Designated States (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

**Published:**

- *with international search report*
- *before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments*

*For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: EFFECT PAINT

(57) Abstract: Emulsion paint composition for obtaining special textile or suede effect comprising a filler at least partly consisting of pre-pigmented spherical aliphatic polyurethane particles. About 3 - 10% of the spherical particles has a particle size between 63 - 90 micrometers and 25 - 40% of the spherical particles has a particle size between 40 - 63 micrometers. Before applying the paint as a semi-opaque top coat the substrate is first coated with an opaque acrylic primer of a corresponding colour and subsequently dried. The top coat is applied by brush in cross way fashion to obtain a suede effect, or it can be applied by roller, while subsequently a tool is used comprising a flat side provided with stiff parallel projecting fibres such as synthetic grass fibres, which are dragged over the fresh paint layer to obtain a linen effect.

WO 2005/090491 A1